

J 376

Bi-compound coating for glass spouts

Description

Graphite-based 2-compound coating: graphite-based epoxy resin and amine-based hardener.

Applications

It enables to reduce the friction coefficient of the spouts and allows to carry the glass homogeneously.

Technical data

Heat the spout up at 60°C for 2 hours to make polymerized.

Reference	designation	Packaging				food certificate number
J376KIT	BI-COMPOUND COATING-J 376-KIT WITH HARDENER AND APPLICATOR	CARTON	12	KIT	2 PCS	

Z.A.E.T - 221, rue Paul Langevin - 60740 Saint-Maximin - FRANCE Tél : +33 (0)3 44 61 76 76 Fax +33 (0)3 44 25 17 78 www.molydal.com

The information contained in this document is given in good faith and does not engage our responsability. To know more, pleas check the safety data sheet